


**STAINLESS STEELS**

	NI	CR	Fe	Si	Mn	C	P	S	Others
17-7 PH	7.130	17.00	Bal	1.00	1.00	0.0900	0.0400	0.0400	Al 1.125
Alloy 20	35.00	20.00	Bal	1.00	2.00	0.0700	0.0450	0.0350	Cu 3.50
302HQ	9.000	18.00	Bal	1.00	2.00	0.0800	0.0450	0.0300	Cu 3.50
303	9.00	18.00	Bal	1.00	2.00	0.1200	0.0400	0.2900	
304	9.00	19.00	Bal	1.00	2.00	0.0800	0.0450	0.0300	
304L	10.00	19.00	Bal	1.00	2.00	0.0300	0.0450	0.0300	
305	11.75	18.00	Bal	1.00	2.00	0.1200	0.0450	0.0300	
309L	13.50	23.00	Bal	1.00	2.00	0.0300	0.0450	0.0300	
310	20.50	25.00	Bal	1.50	2.00	0.2500	0.0450	0.0300	
316L	10.00	17.00	Bal	1.00	2.00	0.0300	0.0450	0.0300	Mo 2.50
317L	13.00	19.00	Bal	1.00	2.00	0.0300	0.0450	0.0300	Mo 3.50
321	9.00	18.00	Bal	1.00	2.00	0.0800	0.0450	0.0300	Ti 5XC
330	35.50	18.50	Bal	1.13	2.00	0.0800	0.0400	0.0300	
347	11.00	18.00	Bal	1.00	2.00	0.0800	0.0450	0.0300	Cb+Ta10XC
410		12.50	Bal	1.00	1.00	0.1500	0.0400	0.0300	
420		13.00	Bal	1.00	1.00	0.1500	0.0400	0.0300	
430		17.00	Bal	1.00	1.00	0.1200	0.0400	0.0300	

Nominal Chemical Compositions